

---

## **NURAFLEX PRIMER WB**

*IKOpro Eco Primer*

### **TECHNICAL DATA SHEET**

---

#### **DESCRIPTION**

Solvent free bitumen primer (water based emulsion) designed to activate and prepare substrates prior to the application of Nuraply bitumen roofing membranes to concrete, plywood, timber, metal, bitumen membranes and brickwork. Drying time approximately 2 hours at 20°C, depending on the substrate and the weather conditions.

#### **SPECIFICATION**

Type: Water based / bitumen emulsion.  
Colour: Black.  
Viscosity: 500-800mPas (25°C, Brookfield spindle 2/5 rpm).  
Solids: 55% approx.  
Cleaner: Water while wet or with White Spirits when dry.  
Stability: Protect from frost. Not freeze-thaw stable.

#### **APPLICATION**

All surfaces must be clean and free from grease, oil, release agents or dust etc. It can be applied using brush, roller or spray. Make sure the primer is dry before applying Nuraply bitumen membranes.

NOTE: Concrete must be cured for a minimum of 27 days and have a moisture content of 5% or less. Plywood and timber must have a moisture content of 18% or less and be of the correct standards.

#### **PACKAGING**

25 litre steel pail

#### **STORAGE**

Store in cool, dry conditions out of direct sunlight between 5° C and 25° C. This product **MUST** be protected from frost.

#### **SHELF LIFE**

12 months in the hermetically sealed packaging under normal temperature conditions and in original containers.

*The information in this product data sheet is based on our experience and testing. It represents the latest information available at the time of printing, but no guarantee of its accuracy is made or implied, nor responsibility taken for use to which this information may be put. We reserve the right to alter or up-date information parameters and formulations at any time without notice.*