

---

## **NURAFLUX PRIMER QD**

*IKOpro Fast Dry Primer*

### **TECHNICAL DATA SHEET**

---

#### **DESCRIPTION**

Quick drying bitumen primer designed to activate and prepare substrates prior to the application of Nuraply bitumen roofing membranes to concrete, plywood, timber, metal, bitumen membranes and brickwork. Drying time approximately 30 minutes, depending on the substrate and the weather conditions.

#### **SPECIFICATION**

Type: Solvent based / bitumen emulsion.  
Colour: Black.  
Viscosity: +/- 7,000cPs (25°C, Brookfield spindle 6 20 rpm).  
Solids: 65% approx.  
Cleaner: White Spirits.  
Stability: Protect from frost. Not freeze-thaw stable.

#### **APPLICATION**

All surfaces must be clean and free from grease, oil, release agents or dust etc. It can be applied using brush, roller or spray. Make sure the primer is dry before applying Nuraply bitumen membranes.

NOTE: Concrete must be cured for a minimum of 27 days and have a moisture content of 5% or less. Plywood and timber must have a moisture content of 18% or less and be of the correct standards.

#### **PACKAGING**

25 litre steel pail

#### **STORAGE**

Store in cool, dry conditions out of direct sunlight between 5° C and 25° C. This product **MUST** be protected from frost.

#### **SHELF LIFE**

3 years in the hermetically sealed packaging under normal temperature conditions and in original containers.

*The information in this product data sheet is based on our experience and testing. It represents the latest information available at the time of printing, but no guarantee of its accuracy is made or implied, nor responsibility taken for use to which this information may be put. We reserve the right to alter or up-date information parameters and formulations at any time without notice.*